

Edition: 01

Issued: 2018-05-15

COAL TAR

FIELD OF APPLICATION

- Plastics, pharmaceuticals and spray products
- Wood saturation and coloring matter
- Road coverings, briquettes and electrodes
- Roofing felt and tar manufacture of boxes
- Fuel and lubricating oil

ORIGIN

Coal tar is removed from oven crude gas immediately after cooling by water. Material is produced at three sites; Raahe, Oxelösund and Luleå.

HEALTH- AND ENVIRONMENTAL EFFECTS

See safety data sheet



Chemical Analysis %

Quality	Value
Benzene	0.2-0.3 %
Toluene	0.2-0.3 %
Xylene	0.2-0.3 %
Naphthalene	10-20 %
Density at 20 C	1.170 g/cm ³ (20 C)
Ash	0.05 %
S	0.60 %
H ₂ O	1.5-2.0 %
Viscosity cSt / 80 o 10	16 %

*Chemical composition is measured by SSAB's laboratory in Raahe, Finland
Method: XRF- analysis*

SSAB Europe Oy, Merox
 P.O Box 93, Rautaruukintie 155
 FI-92101 Raahe, Finland
 T + 46 8 45 45 700
www.merox.org
www.merox.fi
www.merox.se

MEROX